

Tabel de rezistența chimică

Rezistența chimică:

1 = buna

2 = limitat

X = incompatibila

	A		B		C		D		E		F		G		H	
	PVC				Poliuretana		Poliester		Polietilena		Polyamide 6-12		Silicon		PTFE	
	Standard si TRICOCLAIR®		Formula special chimica		NOBELAIR® PU, TECHNOBEL® PU, Tube PU calibré		TECHNOBEL®		Profiline Aqua+ Profiline Aqua+Soft		Tube PA calibré		VITRYL®		Tubes PTFE	
	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C
Acetaldehida	x	x	x	x	x	x	1	2	1	1	2	x	1	1	1	1
Acetat de amid	x	x	x	x	x	x	2	2	1	1	2		x	x	1	1
Acetat de amoniu	1	1	1	1	1	2	1	2	1	1					1	1
Acetat de butil	x	x	x	x	x	x	2	2	1	1	1	1	2	2	1	1
Acetat de cupru					1	2	1	2	1	1			1	1	1	1
Acetat de etil	x	x	x	x	x	x	2	2	2	2	1	1	1	1	1	1
Acetat de izopropil	x	x	x	x	x	x	2	2					2	2	1	1
Acetat de sodiu	1	1	1	1	1	2	1	2	1	1	1	1	1	1	1	1
Acetat de vinil	x	x	x	x			1	2	1	1					1	1
Acetilenă	1	1	1	1	1	1	1	1	1	1	1	1	x	x	1	1
Acetofenonă	x	x	x	x			1	1	1	2	1				1	1
Acetona	x	x	x	x	2	x	x	x	1	2	1	2	2	2	1	1
Acid clorhidric 15%	1	1	1	1	2	x	x	x	1	1	x	x	1	1	1	1
Acid clorhidric concentrat	2	x	2	x	x	x	x	x	1	1	x	x	2	2	1	1
Acid acetic 10%	1	2	1	2	x	x	2	x	1	1	2	x	1	1	1	1
Acid acetic 25%	1	2	1	2	x	x			1	1	x	x	1	1	1	1
Acid acetic 50%	2	x	2	x	x	x			1	1	x	x	x	x	1	1
Acid acetic pur (glaciar)	x	x	2	x	x	x	x	x	x	x	x	x			1	1
Acid arsenic	1		1		x	x			1				2	2	1	1
Acid boric 10%	1	1	1	1	2	x	1	x	1	1	1	x	2	2	1	1
Acid boric fluorură 65 %	1		1		x	x			1				1	1	1	1
Acid bromhidric 10%	1	1	1	1	x	x	x	x	1	1			x	x	1	1
Acid bromhidric 50%	x	x	x	x	x	x	x	x	1	1			x	x	1	1
Acid butiric	1		1		x	x			1	1			x	x	1	1
Acid carbonic	1		1		1				1	1					1	1
Acid cianhidric					2	x	1	x	1	1					1	1
Acid citric	1		1		2	x	1	1	1	1	2	x	x	x	1	1
Acid cloracetic	x	x	x	x	x	x	x	x	1	1	x	x	1	1	1	1
Acid clorosulfonic	x	x	x	x	x	x	x	x	x	x	x	x	x	x	1	1
Acid cromatic 50%	x	x	x	x	x	x	x	x	1	2	x	x	x	x	1	1
Acid fluorhidric 10%	1	x	1		2				2	2			2	2	1	1
Acid fluorhidric 30%	x	x	x	x	2				2	x			2	2	1	1
Acid fluorhidric 40%	x	x	x	x	x	x	x	x	x	x	x	x	2	2	1	1
Acid fluosilicic 30%					x	x	1	x	1	1			x	x	1	1
Acid formic 10%	2	x	x	x	x	x	1	x	1	2			1	1	1	1
Acid formic 80%	x	x	x	x	x	x	2	x	1	1	x	x	2	2	1	1
Acid fosforic 30%	1	1	1	1	2	x	2	x	1	1			1	1	1	1
Acid fosforic 85%	1		1		x	x			1		2	x	x	x	1	1
Acid galic	1		1		x	x			1				1	1	1	1
Acid lactic 10%	x	x	x	x	2	x	1	x	1	2	1	1	1	1	1	1
Acid nitric 25 %	1	x	1		x	x	2		1	1	x	x	x	x	1	1
Acid nitric 40 %	2	x	2		x	x	2		1	2	x	x	x	x	1	1
Acid nitric 60 %	x	x	x		x	x	x	x	2	2	x	x	x	x	1	1
Acid oleic	x	x	x	x	2	x	1	2	1	1	1		x	x	1	1
Acid oxalic	x	x	x	x	x	x	2	x	1	1	1	1			1	1
Acid palmitic	x	x	x	x	1		1	1	1	1	1		1	1	1	1
Acid percloric	1		1		x	x			1				1	1	1	1
Acid picric – soluție					x	x	1	x	1	1			1	1	1	1
Acid silicic					x	x			1				2	2	1	1
Acid stearic	1	1	1	1			1	2	1	1			2	2	1	1
Acid sulfamic 10%	1	1	1	1	1	2	1	1	1	1			1	1	1	1
Acid sulfuric 10 – 30%	1	1	1	1	2	x	2		1	1	x	x	2	2	1	1
Acid sulfuric 40 – 98%	x	x	x	x	x	x	x	x	1	x	x	x	x	x	1	1
Acid sulfuros 75%	x	x	x	x	x	x			1	1			2	2	1	1
Acid sulfuros 10%	2		2		2				1	1			x	x	1	1
Acid tartric	1		1		1		1	2	1	1			1	1	1	1
Acrilat de etil	x	x	x	x			1	2					1	1	1	1
Acrilat de metil							1	2	1	1						
Acilonitril	1	1	1	1	x	x	2	2	1	1			1	1	1	1
AdBlue®	1		1		x		x				2	x				
Alaun	1	1	1	1	1	2	2	2	1	1			1	1	1	1
Alcool amilic	1	2	1	2	2	x	1	2	1	1	1	2	2	2	1	1
Alcool butilic	1	2	1	2	2	x	1	2	x	x	1	2	1	1	1	1
Alcool etilic	1	2	1	2	2	x	1	2	1	2	2	x	1	1	1	1
Alcool izobutilic					2	x	1	2	2	2					1	1
Alcool izopropilic	1	2	1	2	2	x	1	2	1	1	2		2	2	1	1
Alcool metilic 6%	1	1	1	1	1	2	1	2	1	1	x	x	1	1	1	1
Amoniac	x	x	x	x	2	x	x	x	1	1	2	x	1	1	1	1
Amoniac gazos	1		1		2	2	1	2	1	1	1		2	2	1	1
Anhidrida acetica	x	x	x	x	x	x			2	x	2	x	1	1	1	1
Anhidrida carbonica	1	1	1	1	1		1		1	2	1		1	1	1	1
Anhidrida sulfurica uscată					2	x	x	x	2	2			2	2	1	1
Anhidrida sulfuroasa uscată	1	1	1	1	2	x			1	1			1	1	1	1

Tabel de rezistenta chimica

Rezistenta chimica:

1 = buna

2 = limitat

X = incompatibila

	A		B		C		D		E		F		G		H	
	PVC				Poliuretana		Poliester		Polietilena		Polyamide 6-12		Silicon		PTFE	
	Standard si TRICOCCLAIR®		Formula special chimica		NOBELAIR® PU, TECHNOBEL® PU, Tube PU calibré		TECHNOBEL®		Profiline Aqua+ Profiline Aqua+Soft		Tube PA calibré		VITRYL®		Tubes PTFE	
	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C
Anilina (aminobenzen)	x	x	x	x	x	x			1	1	2		1	1	1	1
Apa de clor	1	x	1	x	2	x	x	x	1	2	2	x	2	2	1	1
Apa de javel din comert	1	2	1	2	2	x	x	x	1	1	x	x	1	1	1	1
Apa de mare	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1	1
Apa oxigenata 10%	1	2	1	2	2				1	2	x	x	1	1	1	1
Apa oxigenata 30%	1	x	1	x	2	x	2	x	1	2	x	x	1	1	1	1
Arseniat de cupru					1				1				1	1	1	1
Arseniat de plumb	1		1		1		1	2	1				1	1	1	1
Asfalt	x	x	x	x	x	x							2	2	1	1
Azot	1	1	1	1	1	1	x	x	1	1					1	1
Benzaldehida	x	x	x	x	x	x	x	x	1	x	2	2	x	x	1	1
Benzen	x	x	x	x	x	x			2	x	1	1	x	x	1	1
Benzine	x	x	1	2	1	2	1	2	2	x	1	1	2	2	1	1
Benzine fara plumb	x	x	1	2	1	2	1	2	1	2	1	1			1	1
Bicarbonat de potasiu	1		1		2				1				1	1	1	1
Bicarbonat de sodiu	1		1		2		1	x	1		1		1	1	1	1
Bisulfat de calciu	1	1	1	1	1		1	x	1	1			1	1	1	1
Bisulfat de sodiu	1	1	1	1	x	x	1	x	1				1	1	1	1
Bitum	x	x	x	x							1				1	1
Borat de potasiu	1		1		1		1	1	1				1	1	1	1
Borax (borat de sodiu)	1	2	1		1	2	x	x	1	1	x	x	1	1	1	1
Brom	x	x	x	x	x	x	2	x	x	x	x	x	x	x	1	1
Brombenzen	x	x	x	x			x	x	x	x			x	x	1	1
Bromura de metil	x	x	x	x					x	x					1	1
Bromura de potasiu	1		1		1		1	1	1	1			1	1	1	1
Butan	2	2	2	2	1	1	x	x	1	1	1		2	2	1	1
Carbonat de bariu	1		1		1				1				1	1	1	1
Carbonat de calciu	1		1		1				1				1	1	1	1
Carbonat de magneziu	1		1		1				1				1	1	1	1
Carbonat de potasiu	1		1		x	x	1	2	1	1	1		1	1	1	1
Carbonat de sodiu	1		1		1	2	1	2	1	1	1		1	1	1	1
Ceanat de amoniu	1		1		2				1				1	1	1	1
Cianura de cupru					2				1	1			1	1	1	1
Cianura de potasiu	x	x	x	x	x	x	1	2	1	1			1	1	1	1
Cianura de sodiu	1	2	1	2	x	x	1	2	1	1			1	1	1	1
Ciclohexan	1	1	1	1	2	x	1	x	1	1	1	2	x	x	1	1
Ciclohexanol	x	x	x	x	x	x	x	x	1	1	1	x			1	1
Ciclohexanon	x	x	x	x	x	x	x	x	2	2	1	x	2	2	1	1
Clor umed	x	x	x	x	x	x	x	x	x	x	x	x	x	x	1	1
Clor uscat	x	x	x	x	x	x	x	x	2	x	x	x	x	x	1	1
Clorat de calciu	1		1		1				1				1	1	1	1
Clorat de potasiu	1		1		2				1	1	x		2	2	1	1
Clorat de sodiu	1		1		2		x	x	1	1	x	x	1	1	1	1
Clorbenzen	x	x	x	x	x	x	x	x	2	2	2	x	2	2	1	1
Clorhidrina de glicol							2	x	1	1	x	x			1	1
Cloroform	x	x	x	x	x	x			x	x	x	x	x	x	1	1
Clorura de alil	x	x	x	x	x	x	1	2	x	x			1	1	1	1
Clorura de aluminiu	1	1	1	1	1	2	1	2	1	1	1	1	x	x	1	1
Clorura de amoniu	1	1	1	1	1	2			1	1			1	1	1	1
Clorura de antimoniu 50%	1		1		2		2	2	1				x	x	1	1
Clorura de benzil	x	x	x	x	x	x	1	2	x	x					1	1
Clorura de calciu	1	1	1	1	1	2	1	2	1	1			1	1	1	1
Clorura de cositor	1	1	1	1	1	2	x	x	1	1			x	x	1	1
Clorura de cupru	1	1	1	1	1	2			1	1	2	2	1	1	1	1
Clorura de etil	x	x	x	x	x	x			x	x			x	x	1	1
Clorura de etilena	x	x	x	x	x	x	1	2	x	x	2	2	x	x	1	1
Clorura de fier (II)	1		1		x		1	2	1	1	1		1	1	1	1
Clorura de fier (III)	1	1	1	1	1	2	2	2	1	1	1		1	1	1	1
Clorura de magneziu	1	1	1	1	1	2			1	1			1	1	1	1
Clorura de metil	x	x	x	x	x	x	x	x	x	x	1		x	x	1	1
Clorura de nichel	1	1	1	1	1	2	1	2	1	1			1	1	1	1
Clorura de potasiu	1	1	1	1	1	2	1	2	1	1			1	1	1	1
Clorura de sodiu	1	1	1	1	1	2	1	2	1	1			1	1	1	1
Clorura de sulf	x	x	x	x	1	2	2	2	x	x			x	x	1	1
Clorura de vinil (monomer)	x	x	x	x	x	x			1	1			x	x	1	1
Clorura de zinc	1	1	1	1	1	2	1	2	1	1	1		1	1	1	1
Clorura mercurică	x	x	x	x	1	2	1	2	1	1			1	1	1	1
Coloranti de anilina	1	1	1	1	x	x	2	x	x	x			2	2	1	1
Crezoli	x	x	x	x	x	x	x	x	2	x	x	x	2	2	1	1
Decalină (decahidronaftalină)							1	2	2	x					1	1
Diacetona	x	x	x	x	x	x	x	x	x	x					1	1
Diacetona alcool	x	x	x	x	2	x	x	x	1	1	1		1	1	1	1
Dibutilftanat	x	x	x	x	x	x			x	x			2	2	1	1

Tabel de rezistenta chimica

Rezistenta chimica:

1 = buna

2 = limitat

X = incompatibila

	A		B		C		D		E		F		G		H	
	PVC				Poliuretana		Poliester		Polietilena		Polyamide 6-12		Silicon		PTFE	
	Standard si TRICOCCLAIR®		Formula special chimica		NOBELAIR® PU, TECHNOBEL® PU, Tube PU calibré		TECHNOBEL®		Profiline Aqua + Profiline Aqua + Soft		Tube PA calibré		VITRYL®		Tubes PTFE	
	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C
Dicloretan	x	x	x	x	x	x	x	x	x	x			x	x	1	1
Dicromat de potasiu					2				1	1			1	1	1	1
Dietilamina	x	x	x	x			x	x					1	1	1	1
Dietilena glicol	1		1		1	2	1	2	1	1	2		1	1	1	1
Difenil							1	2	1	1	1				1	1
Dimetilamina	x	x	x	x			x	x	2	2					1	1
Dimetilformamida	x	x	x	x	x	x	x	x	1	2	2				1	1
Dioxid de sulf (gaz)	1		1		x	x			1	1	2		2	2	1	1
Dioxin	x	x	x	x			1	2	2	2	1	2	1	1	1	1
Disulfura de carbon					x	x	x	x	2	2			x	x	1	1
E85	x	x	x	x	1	1	1	2	x	x		x	x	x	1	1
Etanolamina	x	x	x	x	2		x	x	1		1				1	
Eter butilic	1		1		x				1				x	x	1	1
Eter dietilic	x	x	x	x	2				x	x			x	x	1	1
Eter etilic	x	x	x	x	2	x	1	x	x	x			x	x	1	1
Eter izopropilic	x	x	x	x	2	x	2	x	x	x					1	1
Etilbenzen	x	x	x	x	x	x	x	x	2	2					1	1
Etilceluloza							2	x					2	2	1	1
Etilen glicol	2	x	2	x	2	x	1	2	1	x	2		1	1	1	1
Etilen glicol 30%	1	2	1	2	2	x	1	2	1	1	1		1	1	1	1
Etilena					1	1	1	2							1	1
Etilendiamine							x	x	1	1			1	1	1	1
Etilmercaptan	x	x					1	2	x	x					1	1
Fenilhidrazina	x	x	x	x			1	2	x	x					1	1
Fenol	x	x	x	x	x	x	x	x	2	2	2	x	1	1	1	1
Fluor	x	x	x	x	x	x	x	x	1	1	x	x	x	x	1	1
Fluoraluminat de sodiu 10%	1		1		2				1				2	2	1	1
Fluorura de aluminiu	1		1		x	x	1	2	1	1			1	1	1	1
Fluorura de sodiu	1		1		2				1				2	2	1	1
Formaldehida 40%	2	x	2	x	2		2	x	1	1			1	1	1	1
Fosfat de amoniu	1	1	1	1	1		2	x	1	1			1	1	1	1
Fosfat de sodiu	1	1	1	1	2		1	x	1	1	1		1	1	1	1
Freon 11, 113, 114, 12, 21, 22,	x	x	x	x	x	x	1	x	2	2	1	2				
Furan							1	2					2	2	1	1
Furfurol	1	1	1	1	x	x	1	2	x	x					1	1
Gaz carbonic	1	2	1	2	2	x			1		1	x	1	1	1	1
Gaz natural	1	1	1	1	1		1	1	1						1	1
Gelatina	1	1	1	1	1	1	1	1	1	1			1	1	1	1
Glicerina	x	x	x	x	1	1	1	1	1	1	1	2	1	1	1	1
Glicol butilic	x	x	x	x	x	x			1				2	2	1	1
Glucoza	1	1	1	1	1	1	1	1	1	1	1		1	1	1	1
Gudron de huila	x	x	x	x			1	2			1	2			1	1
Hexan	x	x	x	x	2	x	1	x	1	1	1	2	x	x	1	1
Hidrazina	x	x	x	x			x	x	1	1			1	1	1	1
Hidrogen	1	1	1	1	1	1	1	1	1	1					1	1
Hidrogen sulfurat	x	x	x	x	2	x	1	1	1				1	1	1	1
Hidroquinone	1		1				1	1	1	1					1	1
Hidroxid de aluminiu	1		1		2				1				1	1	1	1
Hidroxid de amoniu	1	2	1	2	1				1				1	1	1	1
Hidroxid de calciu	1	1	1	1	1				1				1	1	1	1
Hidroxid de magneziu	1	1	1	1	1				1		1		1	1	1	1
Hidroxid de potasiu	1	2	1	2	2	x	x	x	1	2	2		x	x	1	1
Hipoclorit de calciu 15%	1		1		x	x	x	x	1				x	x	1	1
Hipoclorit de sodiu 15%	1	x	1	x	2	x	x	x	1		x	x	2	2	1	1
Hipoclorit de sodiu 30%	1	x	1	x	x				2		x	x	x	x	1	1
Hiposulfid de sodiu	1	1	1	1	2	x	x	x	1	1			1	1	1	1
Izooctan	x	x	x	x	1	1	x	x	2	x	1				1	1
Kerosen J.P.1	x	x	1	2	1		1	x	x	x	1	2	x	x	1	1
Kerosen J.P.4	x	x	1	2	1		1	x	x	x	1	1	x	x	1	1
Lesie bisulfetica							1	x								
Magneziu					1	1	1	1	1	1					1	1
Matacrlat de metil	x	x	x	x	x	x	1	x	1	1			2	2		
Mercur	1	1	1	1	1		1	1	1	1					1	1
Metafosfat de amoniu	1		1		1				1				1	1	1	1
Metan					1	1	1	1	1	1	1		x	x	1	1
Metiltilacetona	x	x	x	x	x	x	1	x	2	x	1	1	2	2	1	1
Metilzobutilcetona	x	x	x	x	x	x	2	x			1	2	2	2	1	1
Monoclorbenzol	x	x	x	x	x	x			x	x			x	x	1	1
Naftalina	x	x	x	x			2	x	1	2	1		x	x	1	1
Nitrat de amoniu	1	1	1	1	1	2	1	x	1	1			1	1	1	1
Nitrat de argint	1		1		1				1		1		1	1	1	1
Nitrat de cupru					x				1				1	1	1	1
Nitrat de magneziu	1		1		2				1				1	1	1	1

Tabel de rezistenta chimica

Rezistenta chimica:

1 = buna

2 = limitat

X = incompatibila

	A		B		C		D		E		F		G		H	
	PVC				Poliuretana		Poliester		Polietilena		Polyamide 6-12		Silicon		PTFE	
	Standard si TRICOCCLAIR®		Formula special chimica		NOBELAIR® PU, TECHNOBEL® PU, Tube PU calibré		TECHNOBEL®		Profiline Aqua+ Profiline Aqua+ Soft		Tube PA calibré		VITRYL®		Tubes PTFE	
	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C	20°C	50°C
Nitrat de nichel	1		1		2				1				1	1	1	1
Nitrat de potasiu	1		1		1				1				1	1	1	1
Nitrat de sodiu	1	1	1	1	1	2	1	x	1	1			1	1	1	1
Nitrit de sodiu					1				1			2	1	1	1	1
Nitrometan	x	x	x	x			x	x							1	1
Ortodiclorbenzen	x	x	x	x	x	x	x	x					x	x	1	1
Oxid de carbon	1	1	1	1	1	1	1	1	1	1	2	x	1	1		
Oxid de propilena	x	x	x	x			x	x					x	x	1	1
Ozon	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Paradiclorbenzen	x	x	x	x	1		x		x	x	2	x	x	x	1	1
Paraformaldehida					x	x							1	1	1	1
Pentan	2		1						x	x			x	x	1	1
Perborat de sodiu	1		1		x	x	1	x	1	2					1	1
Percloretilena	x	x	x	x	2	x	x	x	x	x	1	x	x	x	1	1
Permanganat de potasiu 10%	1		1		2	x			1	1	x	x	1	1	1	1
Peroxid de azot							1	2					2	2	1	1
Peroxid de sodiu	1	1	1	1	x	x	x	x					x	x	1	1
Persulfat de amoniu	1		1		2				1				1	1	1	1
Petrol lichefiat	x	x	1	2	1	2	1	2	1		1	1	x	x	1	1
Piridina	x	x	x	x	x	x	x	x	2	x	1	x	2	2	1	1
Potasiu concentrat	1	x	1	x	x	x	x	x	1	1	1				1	1
Potasiu diluat 10%	1	x	1	x	2	x	x	x	1	1	1	1			1	1
Propan	x	x	x	x	1	1	1	1	1	1	1	1	x	x	1	1
Propilena							1	1							1	1
Sébaçate d'octyl (Seu)	x	x	x	x			1	x							1	1
Silicat de sodiu	1	1	1	1	2	x	1	2	1	1	1		1	1	1	1
Soda concentrata	1	x	1	x	x	x	x	x	1	1	2	x	2	2	1	1
Soda diluata 10%	1	x	1	x	2	x	x	x	1	1	1	2	1	1	1	1
Stearat de butil	x	x	x	x	1		x	x	x	x			1	1		
Stiren	x	x	x	x	2	x	x	x	2	2			2	2	1	1
Sulfat de aluminiu	1	1	1	1	1	2	1	2	1	1	1		1	1	1	1
Sulfat de amoniu	1	1	1	1	1	2	1	2	1	1	1	2	1	1	1	1
Sulfat de cupru	1	1	1	1	1	2	1	2	1	1	1	1	1	1	1	1
Sulfat de fier	1		1		2				1	1			1	1	1	1
Sulfat de magneziu	1	1	1	1	1	2	1	2	1	1			1	1	1	1
Sulfat de mangan	1		1		2				1				1	1	1	1
Sulfat de nichel	1	1	1	1	1	2	1	2	1	1			1	1	1	1
Sulfat de potasiu	1	1	1	1	1	2	1	2	1	1	1	2	1	1	1	1
Sulfat de sodiu	1	1	1	1	1	2	1	2	1	1			1	1	1	1
Sulfat de zinc	1	1	1	1	1	2	1	1	1	1			1	1	1	1
Sulfat feric	1	1	1	1	1	2	1	1	1	1			1	1	1	1
Sulfura de calciu	1		1		x				1				x	x	1	1
Sulfura de carbon	x	x	x	x	2	x	x	x	x	x	1	x	2	2	1	1
Sulfura de potasiu	1		1		1				1				x	x	1	1
Sulfura de sodiu	1	1	1	1	1		1	2	1	1	1	2	1	1	1	1
Tetraclorura de carbon	x	x	x	x	x	x	x	x	x	x	2	x	2	2	1	1
Tetrahidrofuran	x	x	x	x	x	x	x	x	x	x	1	2	x	x	1	1
Tetralina	x	x	x	x			1	x	2	x	1	2			1	1
Tiosulfat de sodiu	1	1	1	1	2		1	x	1	1			1	1	1	1
Țiței	x	x	1	2	1	2	1	2	2	x	1	1	x	x	1	1
Țiței (ulei ușor)	x	x	x	x			1		1	x	1	1			1	1
Toluen	x	x	x	x	x	x	2	x	1	2	1	2	2	2	1	1
Triclorețan	x	x	x	x	x	x	x	x			2	x	x	x	1	1
Triclorețilena	x	x	x	x	x	x	x	x	x	x	2	x	x	x	1	1
Tricrezilfosfat					2		2	x	1	1						
Tritanolamina	1	1	1	1			x	x			1				1	1
Trixid de sulf	1		1		2				1	x			x	x	1	1
Ulei ASTM 1	x	x	1	2	1	1	1	1			1		1	1		
Ulei ASTM 2		x	1	x	1	2	1	1	1		1					
Ulei ASTM 3	x	x	1	2	1	2	1	2			1		1	1		
Ulei de cereale					2				x	x			1	1	1	1
Ulei de creozot	x	x	1	2			2	x	x	x	1		2	2	1	1
Ulei de lubrifiere	x	x	1	2	1	1	1	1					2	2	1	1
Ulei de ricin	x	x	1	1	1	1	1	1	1	2	1		1	1	1	1
Ulei de silicon	x	x	1	2	1	1	1	1	1	1			1	1	1	1
Ulei de terebentina	x	x	1	2	2	x	2	x	2	x	1	1	x	x	1	1
Ulei mineral	x	x	1	1	1	1	1	1	1	1	1	1	2	2	1	1
Uree 30-50%	1	x	1	x			1		1	1	1		1		1	
Var (lapte de)	1	1	1	1	1	2							1	1	1	1
White spirt	x	x	x	x	1	x	x	x	x	x					1	1
Xilena	x	x	x	x	x	x	2	x	1	x	1	2	2	2	1	1